



Evaluation Report CCMC 13473-R FlexStone

MASTERFORMAT:	07 56 10 02
Evaluation issued:	2014-10-03
Revised:	2016-11-30
Re-evaluation due:	2017-10-03

1. Opinion

It is the opinion of the Canadian Construction Materials Centre (CCMC) that “FlexStone” when used as cold, liquid-applied polyurethane roofing membrane in accordance with the conditions and limitations stated in Section 3 of this Report, complies with the National Building Code of Canada (NBC) 2010:

- Clause 1.2.1.1.(1)(b), Division A, as an alternative solution that achieves at least the minimum level of performance required by Division B in the areas defined by the objectives and functional statements attributed to the following applicable acceptable solutions:
 - Article 9.26.2.1., Material Standards (Roofing Materials)

This opinion is based on CCMC’s evaluation of the technical evidence in Section 4 provided by the Report holder.

Ruling No. 15-04-325 (13473-R) authorizing the use of this product in Ontario, subject to the terms and conditions contained in the Ruling, was made by the Minister of Municipal Affairs and Housing on 2015-09-29 pursuant to s.29 of the Building Code Act, 1992 (see Ruling for terms and conditions). This Ruling is subject to periodic revisions and updates.

2. Description

The product is a roofing membrane system consisting of three distinct layers of liquid-applied polyurethane coatings that, once cured, form a seamless, monolithic roofing membrane.

The basecoat (TUFF) is a water-catalyzed, aromatic urethane, the middle layer (COLORCOAT AR) is a single-component, aliphatic polyurethane, and the top layer (MULT-I-GLAZE) includes acrylic flakes overlaid with a clear coat of single-component, aliphatic polyurethane (isocyanate saturated with polyester backbone).

3. Conditions and Limitations

CCMC’s compliance opinion in Section 1 is bound by “FlexStone” being used in accordance with the conditions and limitations set out below.

- The product must be installed on concrete or plywood substrate that provides positive drainage, where the minimum roof slope is 1 in 50 and up to a maximum roof slope of 1 in 25.
- When the product is used in buildings requiring a fire classification as per the NBC 2010, the product must be tested in accordance to the criteria in CAN/ULC-S107, “Methods of Fire Tests of Roof Coverings” in order to determine the product’s fire classification.
- When the product is used in a roof assembly that requires a fire-resistance rating, the rating must be determined based on the results of tests conducted in conformance with CAN/ULC-S101, “Standard Methods of Fire Endurance Tests of Building Construction and Materials.”
- The substrate must be free of debris, clean and dry prior to installing the product.
- The product must be installed by manufacturer approved installers.
- The product must be installed in accordance with the manufacturer’s installation instructions.
- Usage of the product is limited to areas exposed to light, pedestrian traffic.

- The packaging for the product containers must be identified with the following information:
 - manufacturer’s name or logo; and
 - the phrase “CCMC 13473-R.”

4. Technical Evidence

CCMC’s Technical Guide for “Cold-Applied, Fluid Elastomeric Roofing (Exposed to Light, Pedestrian Traffic)” sets out the nature of the technical evidence required by CCMC to enable it to evaluate a product as an acceptable or alternative solution in compliance with the “National Building Code 2010.” The Report holder has submitted test results for CCMC’s evaluation. Testing was conducted at an independent laboratory recognized by CCMC. The corresponding test results for “FlexStone” are summarized below.

4.1 Performance Requirements

Table 4.1.1 Results of Testing of Physical Properties of “FlexStone”

Property	Material Layer	Unit	Requirement	Result
Linear dimensional change in length	FlexStone	%	$\leq \pm 1$	-0.5
Linear dimensional change in width	FlexStone	%	$\leq \pm 1$	-0.4
Water absorption	Basecoat with middle coat	%	$\leq \pm 3$	2
Tensile strength (tension)	Basecoat	MPa	Report value	2.55
	FlexStone		≥ 1.86	2.92
Elongation	Basecoat	%	Report value	364
	FlexStone		≥ 200	250
Water vapour permeance	FlexStone	ng/Pa·s·m ²	Report value	69.4
Flexibility – mandrel bend	Basecoat	–	No cracking or flaking	Pass
Tear resistance	Basecoat	kN/m	≥ 5.8	10.0
Abrasion resistance	FlexStone	mg	≤ 50	8
Indentation hardness	Basecoat	Durometer units	Report value	58
	FlexStone		82 ± 5	69 ⁽¹⁾
Static puncture	Basecoat	N	4 out of 5 samples ≥ 150 and must pass watertightness test	5 out of 5 at $23 \pm 2^\circ\text{C}$
	Basecoat			5 out of 5 at $-15 \pm 2^\circ\text{C}$
Dynamic impact (puncture)	Basecoat	J	20 out of 24 samples ≥ 9 and pass watertightness	24 out of 24 at $23 \pm 2^\circ\text{C}$
	Basecoat			24 out of 24 at $-15 \pm 2^\circ\text{C}$
Peel adhesion	Basecoat	N/m	≥ 875 concrete	1043
	Basecoat		≥ 525 plywood	1303
Crack bridging as received	Basecoat	–	No evidence of cracking, splitting, pinholes or loss of adhesion	Pass
Crack bridging after heat aging	Basecoat	–	No evidence of cracking, splitting, pinholes or loss of adhesion	Pass

Note to Table 4.1.1:

⁽¹⁾ Hardness property performance deemed acceptable as the product passes static puncture and dynamic impact, and the watertightness test after static puncture and dynamic impact tests.

Table 4.1.2 Results of Testing of Performance Properties of “FlexStone”

Property	Material Layer	Unit	Requirement	Result
Retention of tensile strength after H ₂ O solution	Basecoat	% of original	≥ 70 average	90 (2.30 MPa)
Retention of tensile strength after NaCl solution	Basecoat	% of original	≥ 70 average	85 (2.17 MPa)
Retention of tensile strength after heat aging	Basecoat	% of original	Report value	90 (2.30 MPa)
Retention of tensile strength after heat aging	FlexStone	% of original	≥ 90 average	95 (2.77 MPa)
Retention of elongation after heat aging	Basecoat	%	Report value	56 (204% of original)
Retention of elongation after heat aging	FlexStone	%	≥ 90 average	90 (225% of original)
Retention of tensile strength after accelerated weathering FL/UV – 5000 hours	Basecoat	% of original	Report value	85 (2.17 MPa)
Retention of tensile strength after accelerated weathering FL/UV – 5000 hours	FlexStone	% of original	≥ 90 average	85 ⁽¹⁾ (2.48 MPa)
Retention of elongation after accelerated weathering FL/UV – 5000 hours	Basecoat	%	Report value	47 (171% of original)
Retention of elongation after accelerated weathering FL/UV – 5000 hours	FlexStone	%	≥ 90 average	82 ⁽²⁾ (205% of original)
Glass transition before heat aging	Basecoat	°C	Report value	-49.7
Glass transition after heat aging	Basecoat	°C	Report value	-44.4
Change in glass transition (ΔTg) from before and after heat aging	Basecoat	°C	≤ ± 8	5.3
Glass transition before accelerated weathering FL/UV – 5000 hours	Basecoat	°C	Report value	-49.7
Glass transition after accelerated weathering FL/UV – 5000 hours	Basecoat	°C	Report value	-46.3
Change in glass transition (ΔTg) from before and after accelerated weathering FL/UV – 5000	Basecoat	°C	≤ ± 8	3.4
Watertightness after static puncture	Basecoat	-	No leakage	Pass at 23 ± 2°C
	Basecoat		No leakage	Pass at -15 ± 2°C
Watertightness after dynamic impact (puncture)	Basecoat	-	No leakage	Pass at 23 ± 2°C
	Basecoat		No leakage	Pass at -15 ± 2°C

Notes to Table 4.1.2:

- (1) Property performance deemed acceptable as the tensile strength is maintained at a level above the minimum tensile strength requirement.
- (2) Property performance acceptable as the elongation is maintained at a level above the minimum elongation requirement.

Report Holder

Flexstone Coatings Inc.
1230 West 75 Avenue
Vancouver, BC V6P 3G3

Telephone: (604) 222-8453
Fax: (604) 222-1818

Plant(s)

Fontana, California, USA

Disclaimer

This Report is issued by the Canadian Construction Materials Centre, a program of NRC Construction at the National Research Council of Canada. The Report must be read in the context of the entire CCMC Registry of Product Evaluations, including, without limitation, the introduction therein which sets out important information concerning the interpretation and use of CCMC Evaluation Reports.

Readers must confirm that the Report is current and has not been withdrawn or superseded by a later issue. Please refer to http://www.nrc-cnrc.gc.ca/eng/solutions/advisory/ccmc_index.html, or contact the Canadian Construction Materials Centre, NRC Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone (613) 993-6189. Fax (613) 952-0268.

NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Report are directed to those who have the appropriate degree of experience to use and apply its contents. This Report is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Report. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.

Date modified:
2016-11-30